



SERVICE BULLETIN

Classification: BF94-019	Reference: NTB94-071	Date: July 14, 1994
-----------------------------	-------------------------	------------------------

REMOVAL OF PAINT GUARD FILM ADHESIVE RESIDUE

APPLIED VEHICLE(S): 1994-95 Models

SERVICE INFORMATION

In some cases, thin lines of adhesive residue may be left on the painted body surfaces of vehicles after removing the paint guard film.

To optimize new vehicle presentation, it is important to remove this residue prior to customer delivery.

SERVICE PROCEDURE

While removing the residue, you must use care not to scratch or mar the paint. Use a clean, soft, cotton cloth and the appropriate solvent or non-abrasive polish. Refer to Nissan Technical Bulletin [NTB93-041 (BF93-007)] "Paint Guard Film Removal," issued March 2, 1993, for additional information.

Adhesive Residue

If PGF adhesive residue remains, wipe off with a solvent or a non-abrasive polish:

Use only the following solvents and non-abrasive polishes:

- 3M General Purpose Adhesive Cleaner, P/N 08984
- 3M Prep Solvent-70 [Low-V.O.C. (Volatile Organic Compounds)], P/N 08983
- Meguiar's "Swirl Remove #9," P/N M-0916 (16 ounces) or M-0932 (32 ounces)
- 3M "Perfect-it Glaze," P/N 5995 [light colors] or P/N 5996 [dark colors]
- Isopropyl Alcohol (70%)